

SBM 15 - Cell data sheet


Classification

Brand	Saft
Cell type	SBM 15
Cell P/N	310047172
Capacity at 5 hours rate	15 Ah
IEC Designation	KM15P
According to IEC 60623	



Wiring principle

Normal



Physical data

Overall height	190 mm		
Cell height			
Width	123 mm	Weight per cell	1,2 Kg
Length	-	Block length - 2 cells	74 mm
Block length - 3 cells	109 mm	Block length - 4 cells	-
Block length - 5 cells	-	Block length - 6 cells	-
Block length - 7 cells	-	Block length - 8 cells	-
Block length - 9 cells	-	Block length - 10 cells	-

Construction

Container material	Polypropylene	No. of terminals/polarity	2
Separator type	Grid	Terminal material	Steel
Connection torque	11,0 +/- 1,1 Nm	Vent type	flame arresting vent (small)
Terminal size	M6	Handle	No

Plates

Positive		Negative	
Type of plates	Pocket	Type of plates	Pocket

Electrolyte

Electrolyte type: Renewal	E13	Max/Min	35 mm
Electrolyte type: Initial	E22	Vent oil quantity	
Electrolyte per cell: Liquid	0,3 liters		

Connection

Cable area of internal connection cables	16 mm²	End-lug (and external cable)	10 mm²
--	--------	------------------------------	--------

SAFT confidential and proprietary. The data herein given are for information purposes only and are not binding on SAFT. They may be modified without prior notice. Please contact a SAFT representative in order to obtain confirmation of the above data.

Visit our website at www.saftbatteries.com

(378215) Version: 2.8, Last updated on 12/2019

P 1/3

SBM 15 - Cell data sheet

Charging

Float voltage	1,4 V/Cell	High rate voltage (min)	1,45 V/Cell
Single-level voltage	1,43 V/Cell		

Resistance/Short circuit

Internal resistance	3,67 mOhm	Short circuit current	274 A
---------------------	-----------	-----------------------	-------

Performance data

Current discharge

After prolonged float charge of fully charged cells. Available amperes at +20°C +/- 5°C (+68°F +/- 9°F)

V/Cell	10h	8h	5h	3h	2h	1,5h	1h	30m	20m	15m	10m	5m	1m	30s	5s	1s
1	1,52	1,89	3,00	4,91	7,14	8,82	12,3	15,9	18,5	20,2	23,1	28,0	40,2	46,1	58,0	63,8
1,05	1,51	1,88	2,97	4,83	6,68	8,43	10,8	13,5	16,1	17,6	19,6	23,3	34,6	39,9	49,1	53,1
1,1	1,49	1,85	2,93	4,51	6,20	7,37	8,77	11,0	13,2	14,0	16,2	19,9	29,3	33,6	41,0	43,4
1,14	1,45	1,80	2,82	4,25	5,41	6,15	7,09	8,72	9,9	10,8	12,4	15,6	22,0	24,7	28,8	29,7
1,16	1,41	1,73	2,60	3,93	4,55	4,87	5,90	7,45	8,48	8,91	10,0	12,5	18,4	20,8	23,6	25,2

Power discharge

Available power (W), after prolonged float charged of fully charged cells at +20°C +/- 5°C (+68°F +/- 9°F)

V/Cell	10h	8h	5h	3h	2h	1,5h	1h	30m	20m	15m	10m	5m	1m	30s	5s	1s
1	1,81	2,23	3,50	5,39	7,60	9,24	12,7	16,1	18,6	20,3	23,2	28,0	40,2	46,1	58,0	63,8
1,05	1,80	2,23	3,48	5,42	7,33	9,14	11,6	14,3	17,0	18,5	20,6	24,5	36,4	41,9	51,5	55,7
1,1	1,78	2,20	3,45	5,16	7,00	8,27	9,8	12,1	14,6	15,4	17,9	21,9	32,2	36,9	45,2	47,8
1,14	1,73	2,14	3,33	4,94	6,25	7,09	8,13	10,0	11,3	12,3	14,2	17,8	25,1	28,1	32,8	33,9
1,16	1,69	2,06	3,07	4,61	5,31	5,67	6,86	8,66	9,8	10,3	11,6	14,4	21,4	24,1	27,4	29,2

SBM 15 - Cell data sheet

Kt Factor

Current discharge

After prolonged float charge of fully charged cells. Kt factor at +20°C +/- 5°C (+68°F +/- 9°F)

V/Cell	10h	8h	5h	3h	2h	1,5h	1h	30m	20m	15m	10m	5m	1m	30s	5s	1s
1	9,9	7,94	5,00	3,06	2,10	1,70	1,22	0,95	0,81	0,74	0,65	0,54	0,37	0,33	0,26	0,24
1,05	9,9	7,98	5,05	3,11	2,25	1,78	1,39	1,11	0,93	0,85	0,77	0,64	0,43	0,38	0,31	0,28
1,1	10,1	8,11	5,12	3,33	2,42	2,03	1,71	1,37	1,13	1,07	0,92	0,75	0,51	0,45	0,37	0,35
1,14	10,3	8,33	5,32	3,53	2,77	2,44	2,12	1,72	1,51	1,39	1,21	0,96	0,68	0,61	0,52	0,50
1,16	10,6	8,67	5,78	3,82	3,30	3,08	2,54	2,01	1,77	1,68	1,50	1,20	0,81	0,72	0,64	0,60

Power discharge

Kt factor power, after prolonged float charged of fully charged cells at +20°C +/- 5°C (+68°F +/- 9°F)

V/Cell	10h	8h	5h	3h	2h	1,5h	1h	30m	20m	15m	10m	5m	1m	30s	5s	1s
1	8,28	6,72	4,28	2,78	1,97	1,62	1,18	0,93	0,80	0,74	0,65	0,54	0,37	0,33	0,26	0,24
1,05	8,33	6,74	4,31	2,77	2,05	1,64	1,30	1,05	0,88	0,81	0,73	0,61	0,41	0,36	0,29	0,27
1,1	8,43	6,83	4,35	2,90	2,14	1,81	1,53	1,24	1,03	0,97	0,84	0,68	0,47	0,41	0,33	0,31
1,14	8,66	7,01	4,51	3,04	2,40	2,12	1,84	1,50	1,32	1,22	1,06	0,84	0,60	0,53	0,46	0,44
1,16	8,90	7,29	4,89	3,25	2,82	2,64	2,19	1,73	1,52	1,45	1,29	1,04	0,70	0,62	0,55	0,51